



PVC SCHEDULE 80 FITTINGS AND PIPE

80-2-0123

Performance Engineered & Tested



SPEARS® Schedule 80 PVC product designs combine years of proven experience with computer generated stress analysis to yield the optimum physical structure and performance for each fitting. Material reinforcement is uniformly placed in stress concentration areas for substantially improved pressure handling capability. Resulting products are subjected to numerous verification tests to assure obtaining the very best PVC fittings available.

1/4" Through 14" Availability

Spears® comprehensive line of PVC injection molded fittings and extruded pipe offers a variety of configurations in sizes 1/4" through 14". Schedule 80 fittings are manufactured to ASTM D 2467 and pipe is produced to ASTM D 1785. Spears® exclusive CL150 Flanges are produced in sizes 1/2" - 18" with ANSI B16.5 bolt patterns, plus numerous Unions, Saddles, Transition and Specialty fittings in a variety of sizes.

Exceptional Chemical & Corrosion Resistance

Unlike metal, PVC fittings and pipe never rust, scale, or pit, and will provide many years of maintenance-free service and extended system life.

High Temperature Ratings

PVC thermoplastic can handle fluids at service temperatures up to 140° F (60° C), allowing a wide range of process applications, including corrosive fluids.

Lower Installation Costs

Substantially lower material costs than steel alloys or lined steel, combined with lighter weight and ease of installation, can reduce installation costs by as much as 60% over conventional metal systems.

Higher Flow Capacity

Smooth interior walls result in lower pressure loss and higher volume than conventional metal fittings.

Additional Fabricated Configurations through 36"

Extra large, hard-to-find, and custom configurations are fabricated from NSF® Certified pipe. Fittings are engineered and tested to provide full pressure handling capabilities according to Spears® specifications.

Advanced Design Specialty Fittings

Spears® wide range of innovative, improved products include numerous metal-to-plastic transition fittings and unions with Spears® patented special reinforced (SR) plastic threads.

PVC Valves

SPEARS® PVC Valve products are available for total system compatibility and uniformity; see VALVES IN SPEARS® PRODUCT SOURCE BOOK.



Assessed to ISO 9001: 2015
Certificate number 293

Sample Engineering Specifications

All PVC Schedule 80 pipe and fittings shall be produced by Spears® Manufacturing Company from PVC Type I, cell classification 12454, conforming to ASTM Standard D 1784. All PVC injection molded Schedule 80 fittings and extruded pipe shall be Certified for potable water service by NSF® International. All Schedule 80 fittings shall be manufactured in strict compliance to ASTM D 2467 and Schedule 80 pipe shall be manufactured in strict compliance to ASTM D 1785. All fabricated fittings shall be produced in accordance with Spears® General Specifications for Fabricated Fittings. All PVC flanges shall be designed and manufactured to meet CL150 bolt pattern per ANSI Standard B16.5 and rated for a maximum internal pressure of 150 psi, non-shock at 73° F through size 18".

PROGRESSIVE PRODUCTS FROM SPEARS® INNOVATION & TECHNOLOGY

Visit our website: www.spearsmfg.com

PVC Thermoplastic Pipe Temperature Pressure De-Rating

To determine the maximum internal pressure rating at an elevated temperature, simply multiply the pipe pressure rating at 73° F by the percentage specified for the desired temperature.

System Operating Temperature ° F (° C)	73 (23)	80 (27)	90 (32)	100 (38)	110 (43)	120 (49)	130 (54)	140 (60)
PVC	100%	90%	75%	62%	50%	40%	30%	22%

NOTE: Valves, Unions and Specialty Products have different elevated temperature ratings than pipe.

Typical Material Properties

Properties	ASTM Test Method	PVC	Properties	ASTM Test Method	PVC
Mechanical Properties, 73°F			Flammability		
Specific Gravity, g/cm ³	D 792	1.41	Limited Oxygen Index, %	D 2863	43
Tensile Strength, psi	D 638	7,450	UL 94 Rating	94V-0	
Modulus of Elasticity, psi	D 638	420,000	Other Properties		
Compressive Strength, psi	D 695	9,600	Water Absorption, % 24 hr.	D 570	.05
Flexural Strength, psi	D 790	14,450	Industry Standard Color	White / Dark Gray	
Izod Impact, notched, ft-lb / in	D 256	.75	ASTM Cell Classification	D 1784	12454
Thermal Properties			NSF® Potable Water Approved	YES	
Heat Deflection Temperature, ° F at 66 psi	D 648	170			
Thermal Conductivity, BTU / hr / sq ft / ° F / in	C 177	1.02			
Coefficient of Linear Expansion, in / in / ° F	D 696	2.9 x 10 ⁻⁵			

PVC Chemical Resistance

PVC is generally inert to most mineral acids, bases, salts and paraffinic hydrocarbon solutions. For more information on PVC chemical resistance contact our Technical Services Department at (818) 364-1611.



NOT FOR DISTRIBUTION OF
COMPRESSED AIR OR GAS



SPEARS® MANUFACTURING COMPANY • OPERATIONS

15853 Olden St., Sylmar, CA 91342 • PO Box 9203, Sylmar, CA 91392
(818) 364-1611 • www.spearsmfg.com



SPEARS® DISTRIBUTION CENTERS

ARIZONA

790 South 75th Avenue
Tolleson (Phoenix), AZ 85353
(818) 364-1611 • (800) 862-1499
quotes@spearsmfg.net
CAorder@spearsmfg.net

FLORIDA*

9563 Parksouth Ct.
Orlando, FL 32837
(407) 843-1960 • (800) 327-6390
Fax (407) 425-3563
FLquotes@spearsmfg.net
FLorder@spearsmfg.net

MASSACHUSETTS

240 South Washington St.
Norton (Boston), MA 02766
(717) 938-8844 • (800) 233-0275
Fax (717) 938-6547
PAquotes@spearsmfg.net
PAorder@spearsmfg.net

PENNSYLVANIA*

590 Industrial Dr., Suite 100
Lewisberry (Harrisburg), PA 17339
(717) 938-8844 • (800) 233-0275
Fax (717) 938-6547
PAquotes@spearsmfg.net
PAorder@spearsmfg.net

UTAH

5395 West 1520 South
Salt Lake City, UT 84104
(818) 364-1611 • (800) 862-1499
Fax (818) 367-3014
quotes@spearsmfg.net
CAorder@spearsmfg.net

CALIFORNIA*

15860 Olden St.
Sylmar (Los Angeles), CA 91342
(818) 364-1611 • (800) 862-1499
Fax (818) 367-3014 (Order Dept.)
818-362-1596 (Accounting Dept.)
quotes@spearsmfg.net
CAorder@spearsmfg.net

GEORGIA

4205 Newport Pl., Suite 100
Lawrenceville (Atlanta), GA 30043
(407) 843-1960 • (800) 327-6390
Fax (407) 425-3563
FLquotes@spearsmfg.net
FLorder@spearsmfg.net

MINNESOTA

12700 West French Lake Rd.
Dayton (Minneapolis), MN 55327
(630) 759-7529 • (800) 662-6330
Fax (630) 759-7515
ILquotes@spearsmfg.net
ILorder@spearsmfg.net

Spears®/Associated Marketing*

11500 Roosevelt Blvd.
Building G, Unit 1
Philadelphia, PA 19116
(717) 938-8844 • (800) 233-0275
Fax (717) 938-6547
PAquotes@spearsmfg.net
PAorder@spearsmfg.net

WASHINGTON

4103 "C" St. NE Suite 200
Auburn (Seattle), WA 98002
(818) 364-1611 • (800) 862-1499
Fax (818) 367-3014
quotes@spearsmfg.net
CAorder@spearsmfg.net

Spears®

555 Zephyr St.
Stockton, CA 95206
(818) 364-1611 • (800) 862-1499
Fax (818) 367-3014
quotes@spearsmfg.net
CAorder@spearsmfg.net

ILLINOIS*

1 Gateway Ct., Suite A
Bolingbrook (Chicago), IL 60440
(630) 759-7529 • (800) 662-6330
Fax (630) 759-7515
ILquotes@spearsmfg.net
ILorder@spearsmfg.net

NORTH CAROLINA

3818 Shutterfly Rd.
Charlotte, NC 28217
(717) 938-8844 • (800) 233-0275
Fax (717) 938-6547
PAquotes@spearsmfg.net
PAorder@spearsmfg.net

TEXAS*

1000 Lakeside Parkway
Flower Mound (Dallas), TX 75028
(469) 528-3000 • (800) 441-1437
Fax (469) 528-3001
TXquotes@spearsmfg.net
TXorder@spearsmfg.net

INTERNATIONAL SALES

15853 Olden St
Sylmar (Los Angeles), CA 91342
(818) 364-1611 • (800) 862-1499
Fax (818) 898-3774

COLORADO

4880 Florence St.
Denver, CO 80238
(818) 364-1611 • (800) 862-1499
Fax (818) 367-3014
quotes@spearsmfg.net
CAorder@spearsmfg.net

KENTUCKY

7001 Southside Dr
Louisville, KY 40214
(630) 759-7529 • (800) 662-6330
Fax (630) 759-7515
ILquotes@spearsmfg.net
ILorder@spearsmfg.net

Spears®

303 Gillespie Rd.
Houston, TX 77038
(469) 528-3000 • (800) 441-1437
Fax (469) 528-3001
TXquotes@spearsmfg.net
TXorder@spearsmfg.net

* Customer Service Center